

Table 2 Fiber quality of Hengmian HD008 in regional trial of cotton varieties in Hebei Province during 2016-2017

Year	Upper half mean length (mm)	Fiber strength (cN/tex)	Micronaire	Uniformity (%)	Elongation rate (%)	Reflectance degree (%)	yellowness	Spinning consistency index
2016	29.3	31.9	5.1	86.1	5.5	74.2	6.6	148.0
2017	29.7	30.7	5.2	84.2	5.5	76.0	7.0	136.0
Mean	29.5	31.3	5.2	85.2	5.5	75.1	6.8	142.0